

PRO COLOR FINISH RESIN



Commercial Product Data Sheet

Product Description

Pro Color Finish Resin is a color pigmented, high performance, multi-component, fast curing, flexible PMMA resin for use in the Parapro Roof Membrane, Parapro Flashing, and Terapro Waterproofing & Surfacing Systems.

Product Uses

Pro Color Finish Resin is used as a finish layer for Terapro Flashings, as the finish layer over Terapro Systems surfaced with natural quartz, or as a smooth finish layer into which Terapro Chips are broadcast. Pro Color Finish is also used as an optional finish layer for Parapro Roof Membrane and Parapro Flashing.

Colors

Pro Color Finish Resin is supplied in the following standard colors: Beige 1015, Gray 7044, Terracotta 8081, and Gray 7030. Additional colors are available on a special order basis.

Packaging

Pro Color Finish Resin is supplied in 5-kg (11-lb) and 10-kg (22-lb) resealable drums with locking rings.

Coverage Rates

Reinforced and Unreinforced Terapro Natural Quartz Variants	
Minimum consumption	0.65 kg/m ² (0.060 kg/sf)

Smooth Membrane or Reinforced and Unreinforced Terapro Chips Variants	
Minimum consumption	0.5 kg/m ² (0.046 kg/sf)

Parapro Roof Membrane and Parapro Flashing	
Minimum consumption	0.5 kg/m ² (0.046 kg/sf)

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

Application Conditions

Pro Color Finish Resin can be applied when the ambient temperature is between 32°F (0°C) and 95°F (35°C) and the substrate temperature is between 32°F (0°C) and 122°F (50°C). In warm temperatures, the substrate should be shaded for up to one hour immediately prior to and during application as necessary to maintain the substrate at temperatures below 122°F (50°C).

Storage

Product shelf life is approximately 6 months from ship date. Shelf life will be reduced if product is stored at temperatures above 77°F (25°C). Store indoors in a closed container in a well-ventilated, cool, dry area away from heat, open fire, any ignition source, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store in temperatures below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Materials stored on the job site during application should be kept on a pallet in a shaded, well-ventilated area. In unshaded areas, materials should be covered with a white, reflective tarp in a manner that allows air circulation beneath the tarp.

Handling

Do not smoke. Keep away from open fire, flame or any ignition source. Vapors may form explosive mixtures with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink, or smoke in the application area.

Consult the Material Safety Data Sheet for additional information pertaining to this product.

Personal Protection Equipment (PPE)

Workers must wear a long sleeved shirt with long pants and work boots. Workers must use only butyl rubber or nitrile gloves when mixing or applying this product. Safety glasses with side shields are required for eye protection.

Use local exhaust ventilation to maintain worker exposure below TLV. If the airborne concentration poses a health hazard, becomes irritating, or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. Specific type of respirator will depend of the airborne concentration. Filtering face piece or dust mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

Mixing & Catalyzing

If batch mixing, thoroughly mix the entire drum of resin for 2-3 minutes prior to pouring resin into a second container. Catalyze only the amount of resin that can be used within the anticipated pot life. Add pre-measured catalyst to the resin, stir for 2 minutes using a slow-speed mechanical agitator or mixing stick, and apply to the substrate. The amount of catalyst needed is based on the weight of the resin used, and varies with the ambient temperature as shown in the chart on the back of this sheet.

Pot Life

Pro Color Finish Resin pot life is approximately 15 minutes at 68°F (20°C). Because pot life is in large part dependent on ambient temperature, which constantly changes, actual pot life must be determined in the field. Pot life will be reduced at high temperatures.

Set Times

Minimum set times noted below are approximate, and may vary. The information provided is based on laboratory conditions, and is intended for use as a guideline only. Actual set times and cure times should be established in the field, based on actual field conditions.

Rain Proof at 68°F (20°C): Approximately 30 minutes
Ready for next coat at 68°F (20°C): Approximately 45 minutes
Stress Resistant at 68°F (20°C): Approximately 2 hours

Tool Cleaning

When work is interrupted or completed, tools must be thoroughly cleaned with Pro Prep before any catalyzed resin on the tools hardens.

PRO COLOR FINISH RESIN

Pro Catalyst Mixing Chart

The amount of Pro Catalyst used with Pro Color Finish Resin varies from a minimum of 2% to 6% maximum by weight, depending upon the ambient temperatures as indicated in the following table:

Resin Quantity	2% Catalyst 59°F to 95°F (15°C to 35°C)				4% Catalyst 41°F to 59°F (5°C to 15°C)				6% Catalyst 32°F to 41°F (0°C to 5°C)			
	g	kg	Tblsp.	0.1-kg Bags	g	kg	Tblsp.	0.1-kg Bags	g	kg	Tblsp.	0.1-kg Bags
1.0 kg (1.0 liter)	20	.02	2	n/a	40	.04	4	n/a	60	.06	6	n/a
5.0 kg (5.0 liter)	100	0.1	10	1	200	0.2	20	2	300	0.3	30	3
10.0 kg (10.0 liter)	200	0.2	20	2	400	0.4	40	4	600	0.6	60	6

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.