

TERABASE



Commercial Product Data Sheet

Product Description

Terabase is a high performance modified bitumen base ply designed for use in homogeneous multi-layer modified bitumen plaza deck and green roof membrane systems. Terabase consists of a lightweight random fibrous glass mat impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen.

Product Uses

Terabase is the first ply of Teranap plaza deck and green roof systems, and is lapped 3 inches (7.6 cm) side and end. Terabase can be applied in approved Type IV asphalt or Siplast PA-311 Adhesive. Contact Siplast for specific approval on other product uses.

COMMERCIAL PRODUCT INFORMATION

Unit:	Roll	
Coverage:	1.5 Squares	(13.9 m ²)
Coverage Weight Per Square:	Min: 62 lb	(3.0 kg/m ²)
Roll Length:	Min: 50 ft	(15.24 m)
Roll Width:	Avg: 3.28 ft	(1.00 m)
Thickness:	Avg: 91 mils	(2.3 mm)
	Min: 87 mils	(2.2 mm)
Selvage Width:	N/A	
Selvage Surfacing:	N/A	
Top Surfacing:	Silica Parting Agent	
Back Surfacing:	Silica Parting Agent	

Lines: Two laying lines are placed 3 in (7.6 cm) and 4 in (10.2 cm) from each edge of the material. The line color for this material is white.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palleted rolls is covered with foiled Kraft paper. The palleted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet.
Number of Rolls Per Pallet: 25
Number of Pallets Per Truckload: 18
Minimum Roll Weight: 93 lb (42.2 kg)

Storage and Handling: All Siplast roll waterproofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

TERABASE

Physical and Mechanical Properties

Property (as Manufactured)	Values/Units	Test Method
Thickness (minimum)	87 mils (2.2 mm)	ASTM D 5147 section 5
Thickness (average)	91 mils (2.3 mm)	ASTM D 5147 section 5
¹ Peak Load @ 73°F (average)	30 lbf/inch (5.3 kN/m)	ASTM D 5147 section 6
¹ Peak Load @ 0°F (average)	70 lbf/inch (12.3 kN/m)	ASTM D 5147 section 6
¹ Elongation @ Peak Load, 73°F (average)	3%	ASTM D 5147 section 6
¹ Elongation @ Peak Load, 0°F (average)	3%	ASTM D 5147 section 6
¹ Elongation at 5% Peak Load @ 73°F (average)	50%	ASTM D 5147 section 6
¹ Tear Strength (average)	40 lbf (0.18 kN)	ASTM D 5147 section 7
Water Absorption (maximum)	1%	ASTM D 5147 section 9
Dimensional Stability (maximum)	0.1%	ASTM D 5147 section 10
Low Temperature Flexibility (maximum)	-13°F (-25°C)	ASTM D 5147 section 11
High Temperature Stability (minimum)	250°F (121°C)	ASTM D 5147 section 15

1. The value reported is the lower of either MD or XD.