

TERANAP - 1M SAND



Commercial Product Data Sheet

Product Description

Teranap 1M Sand is a high performance modified bitumen waterproofing ply designed for use in homogeneous multi-layer modified bitumen plaza deck waterproofing membrane systems. Teranap consists of a nonwoven polyester mat impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen. The top and bottom surfaces of the sheet are covered with a silica parting agent.

Product Uses

Teranap 1M Sand is the surface sheet in multi-layer plaza deck waterproofing systems, and is lapped 4 inches (10.2 cm) side and end. Teranap 1M Sand can be applied with a torch, PA-311 Adhesive, or hot asphalt to approved substrates. Contact Siplast for specific approval on other product uses.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

COMMERCIAL PRODUCT INFORMATION

| | | | |
|--------------------|----------------------|--------------------------|--|
| Unit: | Roll | | |
| Coverage: | 0.75 Square | (7.0 m ²) | |
| Weight Per Square: | Min: 116 lb | (5.7 kg/m ²) | |
| Roll Length: | Min: 26.0 ft | (7.92 m) | |
| Roll Width: | Avg: 3.28 | (1.00 m) | |
| Thickness: | Avg: 157 mils | (4.0 mm) | |
| | Min: 154 mils | (3.9 mm) | |
| Selvage Width: | N/A | | |
| Selvage Surfacing: | Silica Parting Agent | | |
| Top Surfacing: | Silica Parting Agent | | |
| Back Surfacing: | Silica Parting Agent | | |

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright in open-topped crates cushioned with cardboard and polystyrene. The top of the palletted rolls is covered with foiled Kraft paper. The palletted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet
Number Rolls Per Pallet: 25
Number Pallets Per Truckload: 18
Minimum Shipping Weight Per Roll: 87 lb (39.5 kg)

Storage and Handling: All Siplast roll waterproofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All waterproofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

TERANAP - 1M SAND

Physical and Mechanical Properties

| Property (as Manufactured) | Values/Units | Test Method |
|--|-----------------------------|---------------------------|
| Thickness (minimum) | 154 mils (3.9 mm) | ASTM D 5147 section 5 |
| Thickness (average) | 157 mils (4.0 mm) | ASTM D 5147 section 5 |
| ¹ Peak Load @ 73°F (average) | 60 lbf/inch (10.5 kN/m) | ASTM D 5147 section 6 |
| ¹ Peak Load @ 0°F (average) | 115 lbf/inch (20.1 kN/m) | ASTM D 5147 section 6 |
| ¹ Elongation @ Peak Load, 73°F (average) | 65% | ASTM D 5147 section 6 |
| ¹ Elongation @ Peak Load, 0°F (average) | 40% | ASTM D 5147 section 6 |
| ¹ Elongation at 5% Peak Load @ 73°F (average) | 100% | ASTM D 5147 section 6 |
| ¹ Tear Strength (average) | 100 lbf (0.45 kN) | ASTM D 5147 section 7 |
| Water Absorption (maximum) | 1% | ASTM D 5147 section 9 |
| Dimensional Stability (maximum) | <0.5% | ASTM D 5147 section 10 |
| Low Temperature Flexibility (maximum) | -13°F (-25°C) | ASTM D 5147 section 11 |
| High Temperature Stability (minimum) | 250°F (121°C) | ASTM D 5147 section 15 |

1. The value reported is the lower of either MD or XD.